

# Technical Data Sheet

## CERACLAD Hollow Core Panel and Corner Products



**Hollow Core Textures:** Click [here](#) to view 21 available textures.

### Product Description

CERACLAD is a fiber cement panel rain screen system manufactured by KMEW Co., Ltd. All panel products meet or exceed the standards of ASTM 1186 and ICC-ES AC-90. CERACLAD Hollow Core products are Type A, Grade I as defined in ASTM 1186.

ICC-ESR #1627

### Panel and Corner Specifications

Panels		Profile
<b>Property</b>		
Dimensions	W: 455mm ± 0.6mm L : 3030mm ±1.0mm T: 16mm ±0.5 mm *Board Formed Concrete is 18mm Thick	
Coverage	1.38 m <sup>2</sup> (15 ft <sup>2</sup> )	
Weight	42 lbs *Board Formed Concrete is 53 lbs	

### Horizontal Preformed Corner

Horizontal Preformed Corner		Profile
<b>Property</b>		
Dimensions	Reveal:91mm (outer) 75mm± 0.5mm (inner) L: 455mm ± 0.6mm T: 16mm ±0.5 mm	
Coverage	0.08 m <sup>2</sup> (0.89 ft <sup>2</sup> )	
Weight	2.5 lbs	

### Vertical Preformed Corner

Vertical Preformed Corner		Profile
<b>Property</b>		
Dimensions	Reveal:91mm (outer) 75mm± 0.5mm (inner) L: 3030mm ±1.0mm T: 16mm ±0.5 mm	
Coverage	0.55 m <sup>2</sup> (5.9 ft <sup>2</sup> )	
Weight	16.5 lbs	

### Fire and Combustibility

CERACLAD has been tested per **ASTM E 84**, Standard Test Method for the Surface Burning Characteristics of Building Products. CERACLAD panel products are rated **Class A**, with a **Smoke Development Classification of 0**, **Flame Spread Classification of 0**.

CERACLAD is a **non-combustible** product in accordance with **CAN/ULC-S114**, Standard Method of Test for Determination of Non-Combustibility in Building Materials.

CERACLAD may be used as part of a **one-hour fire-resistance rated wall assembly** in accordance with testing per **ASTM E 119**. Please consult ESR-1627 for a description of 1 hr rated assemblies.

CERACLAD has met the conditions of **NFPA 268**, Test Method for Determining Ignitability of Exterior Wall Assemblies.

## Physical Properties

Testing of CERA CLAD hollow core per ICC-ES AC 90: Acceptance Criteria for Fiber Cement Siding Used as Exterior Wall Siding and ASTM C 1186: Standard Specification for Flat Fiber Cement Sheets

Property	Test Result	Requirement	Pass/Fail
Dimensional Tolerances: Length, in Width, in Squareness, in Thickness, in	0.00 0.02 0.08 0.00	±0.25 ±0.13 ±0.19 ±0.05	Pass
Flexural Strength (longitudinal direction) Dry (psi) Wet (psi) Freeze/Thaw, % Strength retention Warm Water, % Strength retention	1214 757 93 110	580 580 >80 No Requirement	Pass Pass Pass No Requirement
Density, lb/ft <sup>3</sup>	63.6	No Requirement	No Requirement
Moisture Movement, % 30%-90% relative humidity (MX & XD Average)	0.02	No Requirement	No Requirement
Water Absorption, % by mass	32	No Requirement	No Requirement
Water Tightness	No drop formation	No drop formation	Pass
Warm Water Resistance	No apparent changes	No visible cracks or structural alterations	Pass
Heat/Rain Resistance	No apparent changes	No visible cracks or structural alterations	Pass

## Transverse Loading

Consult ICC-ESR 1627 code compliance report for Allowable Transverse Loads (design pressure / ASD) with 3.0 safety factor applied.

## Green Statistics

<b>Minimum Recycled Content:</b>	<b>44.5%</b>
Pre-Consumer:	30.3%
Post-Consumer:	14.2%

Thermal Properties	
R Value (Resistance)	0.65
U Value (Conductivity)	1.54

## Warranty

**50 Year Limited Warranty:** The Product shall: not incur structural cracking, rot or delaminate under normal use and wear, and shall resist damage caused by termites for a period of 50 years under normal use.

**20 Year Limited Warranty:** The Ceramic Product finish shall (A) retain its color and luster (meaning color fade shall not exceed color No. 1-2 and E= 9.6 in accordance with ISO 105-A02:1990, Test for color fastness- A02: Grey scale for assessing change in color) for color integrity, and shall not significantly (B) peel, (C) incur structural cracking, or (D) chip, for a period of 20 years under normal use.

**15 Year Limited Warranty:** The CREATIV™ Product finish shall not significantly (A) peel, (B) incur structural cracking, or (C) chip, for a period of 15 years under normal use.

\* Please see full warranty for further details on warranty coverage, limitations and exclusions